


All dielectric self-supporting optical cable ASU

Cable Design



Technical data

Fibers of Cable		2-12	14-24
Fiber Model		G.652D	G.652D
Design(StrengthMember+Tube&Filler)		2+1	2+1
Strength Member	Material	FRP	FRP
	Diameter (± 0.05) mm	2.0	2.0
Loose Tube	Material	PBT	PBT
	Diameter (± 0.1) mm	2.1	2.8
	Thickness (± 0.05) mm	0.35	0.4
	Fibers/Tube	2-12	14-24
	The No. of tubes	1	1
Water Blocking Material		Water blocking Yarn	Water blocking Yarn
Rip cord		1	1
Outer Sheath	Material	MDPE	MDPE
	Thickness (± 0.1) mm	1.7	1.7
Cable Diameter (± 0.2) mm		6.8	7.5
Cable Weight (± 10.0) kg/km		35	50

Fibre Color

No.	1	2	3	4	5	6	7	8	9	10	11	12
Color	Blue	Orange	Green	Brown	Gray	White	Red	Black	Yellow	Violet	Pink	Aqua
No.	13	14	15	16	17	18	19	20	21	22	23	24
Color	Blue	Orange	Green	Brown	Gray	White	Red	Black	Yellow	Violet	Pink	Aqua

Note: The colors of the fibers from No. 12 to 24 are all circular chromatograms.

Loose Tube Color

No.	1
Color	Blue

The properties of single mode optical fiber (ITU-T Rec. G.652.D)

Item	Specification
Fiber type	Single mode
Fiber material	Doped silica
Attenuation coefficient	
@ 1310 nm	≤ 0.35 dB/km
@ 1383 nm	≤ 0.32 dB/km
@ 1550 nm	≤ 0.21 dB/km
@ 1625 nm	≤ 0.24 dB/km
Point discontinuity	≤ 0.05 dB
Cable cut-off wavelength	≤ 1260 nm
Zero-dispersion wavelength	1300 ~ 1324 nm
Zero-dispersion slope	≤ 0.092 ps/(nm ² .km)
PMD _Q (Quadrature average*)	≤ 0.2 ps/km ^{1/2}
Mode field diameter @ 1310 nm	9.2±0.4 μm
Core / Clad concentricity error	≤ 0.5 μm
Cladding diameter	125.0 ± 0.7 μm
Cladding non-circularity	$\leq 1.0\%$
Primary coating diameter	245 ± 10 μm
Proof test level	100 kpsi (=0.69 Gpa), 1%
Temperature dependence 0oC~ +70oC @ 1310 & 1550nm	≤ 0.1 dB/km

Main mechanical & environmental performance test

Item	Test Method	Acceptance Condition
Tensile Strength IEC 60794-1-2-E1	- Load: 2.0kn - Length of cable: about 50m	- Fiber strain $\leq 0.33\%$ - Loss change ≤ 0.1 dB @1550 nm - No fiber break and no sheath damage.
Crush Test IEC 60794-1-2-E3	- Load: 2200N/100mm - Load time: 1min	- Loss change ≤ 0.1 dB@1550nm - No fiber break and no sheath damage.
Impact Test IEC 60794-1-2-E4	- Points of impact: 3 - Times of per point: 1 - Impact energy: 5J	- Loss change ≤ 0.1 dB@1550nm - No fiber break and no sheath damage.
Temperature Cycling Test IEC 60794-1-2-F1	- Temperature step: +20°C→-40°C→+70°C	- Loss change ≤ 0.1 dB/km@1550 nm - No fiber break and no sheath damage.

	→+20°C - Time per each step: 12 hrs - Number of cycle: 2	
--	--	--

Sheath marking

The optical fiber drop cable shall have sequentially numbered length marking at intervals of approximately 1 meter. The starting number of ordering length for any coil shall begin with zero meter. The accuracy of the measurement of length marking shall be held within the limits of $\pm 1\%$.